

03 Series Flat Polyurethane Military Topcoats

TECHNICAL DATA SHEET

Product Description

03 Series are chemically cured, two-component, polyurethane topcoat intended for use on exterior application on aircraft and aerospace equipment. When used over properly applied commercial or military primers, it provides excellent protection against weathering, humidity and salt spray.

- Good gloss and color retention
- Compatible with many types of spray equipment
- Resistant to hydraulic fluids, lubricating oils, JP-5 fuel and water
- Service temperature -54°C to 177°C (-65°F to 350°F)

Components



Mix ratio (by volume) for flat colors:

- 03 Series (base component) 3 parts
- 03CAT (catalyst component) 1 part

Specifications



03 Series flat polyurethane military topcoats are qualified to:

- 760-04182
- GP110AEF
- MIL-PRF-85285 Type I
- MMS-420
- MS-461
- WS26052

Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.

Product Compatibility:

03 Series flat polyurethane military topcoats are compatible with the following primers:

- DMS 1786
- MIL-P-53022
- MIL-PRF-23377
- MIL-PRF-85582
- MMS-423
- TT-P-2760

03 Series Flat Polyurethane Military Topcoats

Surface Preparation and Pretreatments



03 Series flat polyurethane military topcoats can be applied over clean, dry, and intact Desoprime™ epoxy and Koroflex® primers. 03 Series polyurethane military topcoats may be applied over the primer with no abrasion if the primer was applied between 4 and 48 hours before top coating. If it is longer, then abrade the primer surface and clean the surface with Desoclean™ 110 mild solvent cleaner. For further information, refer to the technical data sheet for the above mentioned primers.

Instructions for Use



Mixing Instructions:

Thoroughly stir or shake the base component (Part A) before combining to ensure all solids are completely dispersed. Add one volume of catalyst component (Part B) to the three parts of base component (Part A). Do not use the catalyst component (Part B) from another color. Mix by hand stirring, paint shaker or mechanical mixing to ensure the base/catalyst mixture is homogeneous. Do not shake or mechanically mix material for longer than 10 minutes. Thinners are not required for the mixed material. Available thinners for polyurethanes are MIL-T-81772B Type I* (IS-213), VOC Exempt Reducer (IS-256) and Low HAPS thinner (IS-260). Do not add thinners to attempt to compensate for coatings beyond its useful pot life

Note: It is important to condition the paint for 24 hours prior to mixing by placing all materials in the shop or hangar, with ambient temperatures between 13° and 35°C (55° to 95°F). The minimum temperature of the paint components should be 13°C (55°F) prior to mixing.



Induction Time:

Not Required


03 Series Flat Polyurethane Military Topcoats



Viscosity: (23°C/73°F)

- | | |
|----------------|--------------------|
| • #2 Zahn cup | 41 seconds maximum |
| • #4 Ford cup | 30 seconds maximum |
| • ISO 4 cup | 68 seconds maximum |
| • BSB3 cup | 66 seconds maximum |
| • BSB4 cup | 36 seconds maximum |
| • AFNOR #4 cup | 34 seconds maximum |

Note: Viscosities quoted are typical values obtained when using specified mix ratio.



Pot Life:

4 hours @ 21 - 25°C (70 - 77°F)

Application Guidelines

Recommended Application Conditions:

Temperature	15 - 30°C (59 - 86°F)
Relative Humidity	20 - 90%

Application:

Coating may be applied over properly cleaned composite surfaces, epoxy primer coatings or polyurethane coatings. Apply the topcoat using two coats to a total dry film thickness of 1.7 - 2.3 mils. Apply the first coat as a light (mist) coat. Allow the coat to set for 30 - 60 minutes (depending on airflow, temperature and humidity) before applying the second coat to permit solvent evaporation. Apply the second coat in a full wet coat to achieve the desired film thickness. Conventional, Air, Air Assisted Airless, HVLP, Electrostatic spray equipment may be used to apply this material. For your application, please contact the equipment manufacturer for more specific information on Conventional, HVLP or Electrostatic spray applications, and recommendations on hose diameter and lengths.

These application guidelines represent PPG's best advice in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.


03 Series Flat Polyurethane Military Topcoats



Theoretical Coverage:

76.2 square meters/liter at 25 microns dry film (820 square feet/gallon at 1 mil dry film)

Recommended dry film thickness; 42 to 58 microns (1.7 to 2.3 mils)



Dry Film Density:

1.29 - 1.53 grams/cubic centimeter (10.77 - 12.76 pounds/gallon)

Dry Film Weight:

34.7 - 38.7 grams/square meter at 25 microns dry film (0.00711 - 0.00793 pounds/square foot at 1 mil dry film)



Equipment:

03 Series flat polyurethane military topcoats are compatible with all current forms of spray equipment.

Equipment Type	Tip Size	Pot Pressure	Atomization Pressure at the Cap
Electrostatic Air Spray Gun	1.2 mm or 1.5 mm	10 to 20 psi (0.69 to 1.4 bar)	45 to 60 psi (3.1 to 4.1 bar)
Electrostatic Air Assisted Airless Spray Gun	#611 or #613 (Graco Nomenclature)	700 to 1200 psi (48 to 82 bar)	40 to 60 psi (2.8 to 4.1 bar)
High Volume Low Pressure Spray Gun (HVLP)	1.0 mm to 1.4 mm	10 to 20 psi (0.69 to 1.4 bar)	10 psi maximum (0.69 bar)
Conventional Air Spray Gun	1.2 mm to 1.8 mm	10 to 20 psi (0.69 to 1.4 bar)	45 to 60 psi (3.1 to 4.1 bar)

Equipment Cleaning:

Clean spray equipment as soon as possible after use. Flush spray equipment with IS-213 Polyurethane Reducer (MIL-T-81772 Type I) DeSoto® CN20, DeSoto® CN44, or Desoclean™ 45 high performance solvent cleaner. Once material is fully cured, use an approved chemical paint removal system to strip off coating.

03 Series Flat Polyurethane Military Topcoats

Physical Properties (product)



Color: Available in Federal Standard 595 color chips
 (Fed Standard 34095 cannot be certified to any material specification)



Gloss: <10 G.U at 85°



Dry Times	22 - 28°C (71 - 84°F)
Set to Touch	6 hours min
Dry to Tape	12 hours minimum
Dry Hard	12 hours maximum
Full Cure	14 days

Forced Dry Schedule: For dry to stack conditions only. Allow a minimum of 30 minutes flash off time at ambient temperatures* prior to exposing painted parts to high temperatures. Complete testing should be done prior to use. Below are suggested starting points. Other variables may affect these cure schedules.

Temperature	Time
49°C (120°F)	45 minutes
60°C (140°F)	30 minutes
71°C (160°F)	20 minutes
82°C (180°F)	15 minutes

Note: Ambient temperatures are defined as 70° ± 10°F and 50% ± 10% relative humidity.

Note: The cure rates are not affected by humidity.

Note: The times listed above are dependent upon film thickness, airflow, and spray technique. Lower film thickness, better airflow, spraying "dry" will decrease the dry-to-tape, and time between coats.

03 Series Flat Polyurethane Military Topcoats

VOC

VOC:

Mixed, ready to use VOC (EPA method 24) for all colors is 420 grams/liter.

Base Component	441 grams/liter
Activator Component	282 grams/liter



Flash point closed cup:

Base Component	24°C (76°F)
Activator Component	58°C (136°F)

Shelf Life:

12 months from date of manufacture to most OEM material specifications. Consult the specification to verify shelf life requirements.

24 months from date of manufacture for PRC-DeSoto Standard.

Note: Shelf life is provided for original, unopened containers.

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

Note: When procuring to a qualified material specification, follow those storage instructions.

03 Series Flat Polyurethane Military Topcoats

Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

Additional information can be found at: www.ppgaerospace.com

For sales and ordering information call the local PPG office at the numbers listed below:

Asia Pacific

ASC – Australia

Tel 61 (3) 9335 1557
Fax 61 (3) 9335 3490

ASC – Japan

Tel 81 561 35 5200
Fax 81 561 35 5201

ASC – South East Asia

Tel 65 6861 1119
Fax 65 6861 6162

ASC – Suzhou

Tel (86-512) 6661 5858
Fax (86-512) 6661 6868

ASC – Tianjin

Tel (86-022) 2482 8625
Fax (86-022) 2482 8600

Americas

1 (818) 362-6711 or 1-800-AEROMIX

Europe and Middle East

ASC – Central Europe

Tel 49 (40) 742 193 10
Fax 49 (40) 742 139 69

ASC – Middle East & India

Tel (971) 4 883 9666
Fax (971) 4 883 9665

ASC – North Europe

Tel 44 (0) 1388 770222
Fax 44 (0) 1388 770288

ASC – South Europe

Tel 33 (0) 235 53 43 71
Fax 33 (0) 235 53 54 44

Desoclean, Desoprime, DeSoto, and Koroflex are trademarks of PRC-DeSoto International, Inc.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PRC-DeSoto International,
Inc.
12780 San Fernando Road
Sylmar, CA 91342
www.ppgaerospace.com

Issue Date: 11/16
Lit: 4153